



# Selectarc Inox 316L

Stainless Steel  
Rutile Electrode

## Classification

AWS A5.4 : E316L-17  
ISO 3581-A : E 19 12 3 L R 3 2

EN 1600 : E 19 12 3 L R 3 2

## Description & Applications

Low carbon Rutile-basic-coated Mo containing austenitic stainless steel electrode with approx. 8% ferrite. Coating with very low moisture pick-up. Soft fusion without spatters, very easy slag removal, exceptional bead appearance, easy restriking. Exceptional welding in position. For welding and cladding on austenitic Cr-Ni-Mo stainless steels and clad plates. Applied for service temperatures from -120°C up to +400°C in the chemical and petrochemical industries, in refineries, in the food industries and for ship building to weld pipes, tanks, heat exchangers.....

## Base materials

### Stainless steels for general use:

UNS	Alloy	EN 10088	Material N°	UGINE
S31600	316	X5CrNiMo17-22-2	1.4401	UGINOX 17-10 M
S31603	316L	X2CrNiMo17-12-2	1.4404	UGINOX 18-11 ML
J92900		G-X5CrNiMo 19 11 2	1.4408	
S31635	316Ti	X6CrNiMoTi17-12-2	1.4571	UGINOX 17-11 MT
S31635	316Ti	X10CrNiMoTi18-12	1.4573	
S31640	316Cb	X6NiCrMoNb17-12-2	1.4580	
		G-X5CrNiMoNb19-11-2	1.4581	

## Typical Weld Metal Composition ( % )

C	Si	Mn	Cr	Ni	Mo	Fe
<0.03	0.8	0.7	18.5	12.2	2.8	Rem.

## All Weld Metal Mechanical Properties

R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )
450	580	40	+20°C 70 -120°C 40

## Welding Current & Instructions

Electrode	ØxL ( mm )	2,0x300	2,5x350	3,2x350	4,0x450
Current	( A )	45	75	110	140

Redrying at 250°C during 1h, if necessary. Interpass temperature : < 150°C.

ind.12



= + ~ 70V

**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.